

Huta Bankowa Sp. z o.o.

Declaration of Performance No. 001/CPR/2018

Unique identification code of the product type (round bars/equal-sided angles/bulb bars made of S235JR steel acc. to EN 10025-2): **1.0038**

Intended use or uses:
in metal structures or composite metal and concrete structures.

Manufacturer: **Huta Bankowa Sp. z o.o.**
ul. Sobieskiego 24
41-600 Dąbrowa Górnicza, POLAND
<http://www.hutabankowa.pl/deklaracje.php>

System of assessment and verification of constancy of performance: **system 2+**

Harmonised standard: **EN 10025-1:2004**


Notified body: Zakłady Badań i Atestacji „ZETOM” im. Prof. F. Stauba
w Katowicach Sp. z o.o., notified body number 1436
inspected the production plant and the factory production
control in the system 2+ and issued the Certificate of Conformity
of the factory production control no.
1436-CPR-0009

Declared performance characteristics in accordance with the Table no. 1.

The performance of the product identified above is in conformity with the declared performances. This Declaration of Performance has been issued in accordance with the (EU) Regulation no. 305/2011 under the sole responsibility of the manufacturer identified hereinabove.

Signed on behalf of the manufacturer:
Anna Gwóźdź-Kotnis
Production Development and Planning Manager

KIEROWNIK DZIAŁU
Rozwoju i Planowania Produkcji


Anna Gwóźdź-Kotnis

Dąbrowa Górnicza, 07/12/2018

Table no. 1

Essential characteristics				Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Round bars		EN 10060		EN 10025-1:2004		
	Equal-sided angles		EN 10056-2				
	Bulb bars		EN 10067				
Yield strength	Nominal thickness [mm]		Value [MPa]				
	>	≤	Min				
		16	235				
	16	40	225				
	80	100	215				
	100	150	195				
	150	200	185				
Tensile strength	Nominal thickness [mm]		Value [MPa]				
	>	≤	min	max			
	=3	100	360	510			
	100	150	350	500			
	150	250	340	490			
Elongation	Nominal thickness [mm]		Value [%]				
	>	≤	Min				
	=3	40	26				
	63	100	24				
	100	150	22				
Impact strength (KV)	Nominal thickness [mm]		Value [J]				
	>	≤	min				
	150	250	27 at +20°C				
Weldability	Nominal thickness [mm]		CEV [%]				
	>	≤	max				
		30	0.35				
	40	150	0.38				
Chemical composition:	Maximum element content [%]						
	C	Si	Mn	P	S	N	Cu
	0.20	-	1.40	0.040	0.040	0.012	0.55